


GORILLA GRIP® II



REMOVE liner from adhesive side of material before cutting. Feed Material into cutter so that the carrier is on the bottom




PREHEAT & POSITION—
 Preheat garment for 10 seconds, prior to application. Position weeded design on garment with the carrier side up (*reads left to right*). Place cover sheet over graphic.

Recommended Fabrics:

100% cotton – *excludes hot pink*
 100% polyester
 Poly/cotton blends
 Lycra®/ Spandex blends
 Woven nylon
 Nylon knits
 Nylon meshes - micro, tricot, mini, reversible
 Cordura®

Due to the combination of fabrics, weaves, coatings and dyes used in the textile industry, Stahls' recommends and provides samples of our materials and medias for testing. Hot Pink is not recommended for Cotton fabrics.



CUT LOGO, words or numbers in reverse (*mirror image*).



HEAT APPLY—
 Temperature: 320°F; 160°C
 Time: 2 seconds
 Pressure: light #2 on Hotronix®

Tip: A Teflon Pillow or Print Perfect Pad is recommended for even pressure when working around zippers, buttons, heavy seams or mesh reversible jerseys.

Accessories Required:

Cover Sheet
 Weeder® or Tweezers

Cutting Notes

You should always test cut prior to any production run. For optimal cutting and weeding, maintain a line thickness of at least 1/8" for lettering & logos.



WEED away excess material leaving only the desired graphic on the carrier for heat transferring.



PEEL COLD— The design must cool completely before peeling the carrier.

FINAL APPLICATION—
 Place cover sheet over graphic and reseal for 10 seconds.

Care Instructions

Machine wash using mild detergent. Do not use bleach. Dry at a normal dryer setting on household machines. Do not iron directly onto GORILLA GRIP® II.

Multi-Color Designs

Apply background for 2 seconds; Peel COLD. Apply foreground for 2 seconds; Peel COLD. Cover with Kraft Paper and heat seal for 10 seconds at 320° F, light pressure.

CUTTER GUIDELINES

CUTTER	BLADE	FORCE	OFFSET	SPEED
Roland GX-24	60° / 45°	80-100g / 100-150g	.30 / .25	50cm/s
Ioline 100	45°	150g	.15	12:30
Ioline 300	30°	100g	.15	12:15

All technical information and recommendations are based on tests we believe to be reliable. However, we cannot guarantee performance for conditions not under manufacturer's control. Before using, please determine the suitability of product for its intended use. The user assumes all risk and liability whatsoever in connection with the use of this product. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective by manufacturer.

CAD-CUT, GORILLA GRIP II, & Hotronix are trademarks & ® trademarks of Stahls' ID Direct™ with one or more patents or patents pending.
 © Stahls' ID Direct™ 2012 - All International Rights Reserved