

INSTRUCTIONS FOR USING Wool & Acrylic Felt

To Order: 800.4.STAHLs • Fax: 800.346.2216
International: 586.772.5551 • Canada: 800.521.5255
StahlsID.com • StahlsCanada.com
for current application instructions visit us online

IMPORTANT

The adhesive used on Stahls' Felt is a non-permanent, tack-only adhesive. The Felt should be sewn (usually with a straight stitch) after heat application. A number of our customers choose to heat apply Felt and not sew. If that method is used, there is no guarantee regarding permanent adhesion.

Also, because wool Felt is a non-woven, it will "distress" or wear in its own unique way with time and washing.

Permanent adhesion is not guaranteed without sewing



Hotronix is a registered trademark of Stahls' ID Direct with one or more patents or patents pending. © Stahls' ID Direct 2008

All technical information and recommendations are based on tests we believe to be reliable. However, we cannot guarantee performance for conditions not under manufacturer's control. Before using, please determine the suitability of product for its intended use. The user assumes all risk and liability whatsoever in connection with the use of this product. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective by manufacturer.

STAHLs' ID direct™
StahlsID.com
800.4.STAHLs

STAHLs' CANADA
StahlsCanada.com
800.521.5255

9992516 F-01 02/09

INSTRUCTIONS FOR USING Wool & Acrylic Felt

To Order: 800.4.STAHLs • Fax: 800.346.2216
International: 586.772.5551 • Canada: 800.521.5255
StahlsID.com • StahlsCanada.com
for current application instructions visit us online

IMPORTANT

The adhesive used on Stahls' Felt is a non-permanent, tack-only adhesive. The Felt should be sewn (usually with a straight stitch) after heat application. A number of our customers choose to heat apply Felt and not sew. If that method is used, there is no guarantee regarding permanent adhesion.

Also, because wool Felt is a non-woven, it will "distress" or wear in its own unique way with time and washing.

Permanent adhesion is not guaranteed without sewing



Hotronix is a registered trademark of Stahls' ID Direct with one or more patents or patents pending. © Stahls' ID Direct 2008

All technical information and recommendations are based on tests we believe to be reliable. However, we cannot guarantee performance for conditions not under manufacturer's control. Before using, please determine the suitability of product for its intended use. The user assumes all risk and liability whatsoever in connection with the use of this product. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective by manufacturer.

STAHLs' ID direct™
StahlsID.com
800.4.STAHLs

STAHLs' CANADA
StahlsCanada.com
800.521.5255

9992516 F-01 02/09

APPLICATION

Tack Felt to garment before sewing.

Temperature: 350° F; 177° C

Time: 10 seconds (20 seconds. if not sewing)

Pressure: Firm (#7)

2-COLOR APPLICATION

Add 5 seconds to the dwell time.

SEWING

Felt must be sewn to stay on permanently.

TIP

If necessary, to flatten out Felt and ensure proper alignment, tack for 2-3 seconds first.

Then complete steps 1 and 2.

FELT CARE INSTRUCTIONS: Machine wash using warm water only (under 110° F) and mild detergent. Do not use bleach. Dry at normal dryer settings on household machines. Felt can be ironed.

APPLICATION

Tack Felt to garment before sewing.

Temperature: 350° F; 177° C

Time: 10 seconds (20 seconds. if not sewing)

Pressure: Firm (#7)

2-COLOR APPLICATION

Add 5 seconds to the dwell time.

SEWING

Felt must be sewn to stay on permanently.

TIP

If necessary, to flatten out Felt and ensure proper alignment, tack for 2-3 seconds first.

Then complete steps 1 and 2.

FELT CARE INSTRUCTIONS: Machine wash using warm water only (under 110° F) and mild detergent. Do not use bleach. Dry at normal dryer settings on household machines. Felt can be ironed.